

Specification

Low Melt Polyester Staple Fiber, 4 den x 51 mm

Raw white, semi dull, bi-component sheath and core type

Properties	Unit	Range of Control
Denier	g/9000 M	4.40 +/- 0.35
Strength	g/De	2.8 +/- 0.7
Elongation	%	48 +/- 12
Crimp Number	Ea/Inch	10 +/- 3
Oil Pick-Up	%	< 0.2
Bone Dry Shrinkage	%	8.00 +/- 2.00
Melting Point	° C	110° C
Fiber Length	mm	50.5 +/- 4.00