

## Specification

Low Melt Polyester Staple Fiber, 6 den x 51 mm

Raw white, semi dull, bi-component sheath and core type

Properties	Unit	Range of Control
Denier	g/9000 M	5.75 +/- 0.75
Strength	g/De	3 +/- 1
Elongation	%	51.5 +/- 16.5
Crimp Number	Ea/Inch	8 +/- 3
Crimp Degree	%	14 +/- 6
Oil Pick-Up	%	0.135 +/- 0.025
Heat Shrinkage	%	6 +/- 1
Melting Point	° C	110° C
Fiber Length	mm	Buyer's option