

Specification

Regenerated Staple Fiber, 15 den x 64 mm

Dry finish type

Properties	Unit	Range of Control
Denier	g/9000 M	17.00 +/- 1.00
Tenacity	g/De	4.10 +/- 0.50
Elongation	%	42.00 +/- 5.00
Crimp Number	Ea/Inch	8.50 +/- 1.50
Oil Pick-up	%	0.20 +/- 0.05
Shrinkage	%	42.00 +/- 5.00
Melting Point	° C	260° C +/- 5.00
Fiber Length	mm	64.00 +/- 5.00