

Specification

RPET Resin 825

Properties	Unit	Range of Control
Intrinsic Viscosity	dl/g	0.82 +/- 0.03
Granulate size	mm	2-4 mm
Humidity	%	≤ 0.2 %
Colour	L	> 65
	a	-5 up to 0
	b	-3 up to +4
Acetaldehyd	ppm	≤ 1
Bulk density	kg/m ³	ca. 900
Dust content	%	< 0.01
Filter unit	my	50
Melting point	°C	ca. 250

Hertex AG | Oststrasse 8 | 8500 Frauenfeld | Switzerland

T +41 (0) 52 721 40 55 | F +41 (0) 52 722 11 15 | E-Mail info@hertex.ch | www.hertex.ch